

# Plastifloor® 418 self-leveling floor with membrane and partly flakes

Easy to install, 2h after installation you can drive on it



## 2nd sealer

Plastifloor® 522

0.4 kg/m<sup>2</sup>

clear

## 1st sealer

Plastifloor® 522

0.4 kg/m<sup>2</sup>

clear

intermediate

grinding

## Coating

Plastifloor® 418

1.2 kg/m<sup>2</sup>

1:1 with SL filler

5 % pigment paste

with colour flakes partly  
broadcast

## Membrane

Plastifloor® 332

1.2 kg/m<sup>2</sup>

1:1 with SL filler

fully broadcast

with quartz sand 0.6 – 1.2 mm

## Primer

Plastifloor® 112

0.5 kg/m<sup>2</sup>

slightly broadcast

with quartz sand 0.6 – 1.2 mm